

General Specifications

| | |
|-----------------------|---------------------------|
| Overall Thickness: | 2.0 mm |
| Wear Layer Thickness: | 0.2 mm (8 mil) |
| Product Type: | Glue Down LVT |
| Dimensions: | 6" x 48" |
| Finish: | High Performance Urethane |
| Surface: | Embossed w/ Straight Edge |
| Residential Warranty: | 15 Years |
| Carton Quantity: | 20 Pieces (40 sq. ft.) |
| Carton Weight: | 31 lbs. |
| Cartons / Pallet: | 55 |

Technical Specifications

| | |
|---|--|
| ASTM F1700 - Solid Vinyl Tile Specification: | Class III, Type B |
| ASTM F2055 - Size: | Passes, ± 0.4 mm |
| ASTM F387 - Product Thickness: | Passes, ± 0.13 mm |
| ASTM F2055 - Squareness: | Passes, ± 0.25 mm |
| ASTM F1914 - Residual Indentation: | Passes, ≤ 0.2 mm |
| ASTM F137 - Flexibility: | Passes, 25.4 mm mandrel |
| ASTM F2199 - Dimensional Stability: | Passes, < 0.5 mm / lin. ft. |
| ASTM F925 - Chemical Resistance: | Passes ASTM F1700 requirements |
| ASTM F1514 - Resistance to Heat: | Passes, $< \Delta E 8$ |
| ASTM F1515 - Resistance to Light: | Passes, $< \Delta E 8$ |
| ASTM F970 - Static Load (Modified): | Passes, ≤ 0.13 mm indent, 1600 lbs. |
| ASTM D2047 - Slip Resistance: | Passes, > 0.5 SCOF (no ramps) |
| ASTM E648 (NFPA 253) - Critical Radiant Flux: | Class 1, > 0.45 W/cm ² |
| ASTM E662 (NFPA 258) - Smoke Density: | Passes, < 450 |

Disclaimer: These test results were independently tested, using material from standard production, in accordance with product-specific standard test methods. Physical and performance testing may vary, within tolerances, depending on the testing apparatus and/or production lot used. Be sure to use the most recently published versions of all reference documents, specifications and test methods. To purchase the most recent version of the above mentioned ASTM and ISO standards, please visit www.astm.org. or www.iso.org, respectively. Test reports are available upon request.