

## Natchez 4.5mm | LLT

**Technical Data Sheet** 

## **General Specifications**

Overall Thickness: 4.5 mm

Wear Layer Thickness: 0.5 mm (20 mil)

Product Type: Loose Lay LVT (LLT)

Dimensions: 6" x 48"

Finish: High Performance Urethane

Surface: Embossed w/ Microbevel

Residential Warranty: Lifetime
Heavy Commercial Warranty: 15 Years

Carton Quantity: 10 Pieces (20 sq. ft.)

Carton Weight: 33 lbs.
Cartons / Pallet: 54

## **Technical Specifications**

ASTM F1700 - Solid Vinyl Tile Specification: Class III, Type B

ASTM F2055 - Size: Passes, ± 0.4 mm

ASTM F387 - Product Thickness: Passes, ± 0.13 mm

ASTM F410 - Wear Layer Thickness: Passes, ≥ 0.5 mm

ASTM F2055 - Squareness: Passes, ± 0.25 mm

ASTM F1914 - Residual Indentation: Passes, ≤ 0.2 mm

ASTM F137 - Flexibility: Passes, 25.4 mm mandrel

ASTM F2199 - Dimensional Stability: Passes, < 0.5 mm / lin. ft.

ASTM F925 - Chemical Resistance: Passes ASTM F1700 requirements

ASTM F1514 - Resistance to Heat: Passes,  $< \Delta E 8$ ASTM F1515 - Resistance to Light: Passes,  $< \Delta E 8$ 

ASTM F970 - Static Load (Modified): ≤ 0.13 mm indent, 1300 lbs.

ASTM E648 (NFPA 253) - Critical Radiant Flux: Class 1, > 0.45 W/cm2

ASTM E662 (NFPA 258) - Smoke Density: Passes, < 450

ASTM D2047 - Static Coefficient of Friction: Passes, > 0.5 SCOF (no ramps)

ASTM E492 / E989 - Impact Insulation Class: IIC 52\$

ASTM E90 / E413 - Sound Transmission Class: STC 61\$

ASTM E2179 - Delta Impact Insulation Class:  $\Delta$ IIC 12\*

\* 6" concrete | §6" concrete, gypsum ceiling

**Disclaimer:** These test results were independently tested, using material from standard production, in accordance with product-specific standard test methods. Physical and performance testing may vary, within tolerances, depending on the testing apparatus and/or production lot used. Be sure to use the most recently published versions of all reference documents, specifications and test methods. To purchase the most recent version of the above mentioned ASTM and ISO standards, please visit www.astm.org. or www.iso.org, respectively. Test reports are available upon request.